



Seal Bond® 95 Application Instructions

APPLICATION: To improve adhesion performance make certain that all surfaces are clean and free of dirt, dust, grease, oil, frost, curing compounds and other contaminants. Seal Bond® 95 should be conditioned to room temperature before use. This product can be used at temperatures as low as 30° F.

Apply adhesive to pedestal using method preferred by professional installer of access flooring. Pedestal should be pressed firmly onto the floor to ensure complete coverage of the pedestal base. Optimally, adhesive should exude from all four sides of the pedestal base.

Seal Bond® 95 will typically reach full cure in 7-10 days. If concrete is sealed or coated, full cure of the adhesive may be delayed and adhesion performance may vary. Contact the manufacturer for additional information regarding concrete sealers and the use of Seal Bond® 95.

Adhesive performance requirements for job specific floor installations need to be determined by the Access Floor Manufacturer or designated Engineering Company.

Adhesive manufacturer recommends that the responsible party performs a CISCA approved overturning moment test at the actual job site to verify that the "system" (floor surface, sealer if present, adhesive and specific pedestal, etc.) meets the expected performance requirements.

p (800) 252-4144

f (616) 850-0530

www.seal-bond.com

our innovations...your success